



PO Box 6256
Mobile AL, 36606
1-800-771-6643

PRODUCT DATA SHEET

Acrylic Wall Coat 2000

DESCRIPTION

Acrylic Wall Coat 2000 (AWC 2000) is an acrylic wall coating, flat in finish, that provides excellent flexibility, durability, and weather resistance. The AWC 2000 is suitable for many wall substrates including precast, or poured-in-place concrete, block, and stucco.

ADVANTAGES

- Long Lasting Durable elastomeric finish.
- Contains a strong mildewcide / fungicide.
- Excellent adhesion to various substrates.
- Superior resistance to dirt pick-up.
- Easy to use, easy clean up, non-toxic and VOC compliant water based coating.

BASIC USES

Acrylic Wall Coat 2000 (AWC 2000) is suitable for interior or exterior wall finishes including wood, precast, or poured in place concrete, block, and stucco.

INSTALLATION

All surfaces to be coated must be cleaned properly. Power washing is recommended. Any existing coating must be checked for good adhesion. Before application, any loosely adhered coating must be removed and bare surfaces must be prepared, cleaned and checked for compatibility.

Acrylic Wall Coat 2000 (AWC 2000) is ready to use. Thinning is not required or recommended.

- Brush: Use a nylon or polyester brush. Do not over-brush as this can cause pinholes and air bubbles.
- Roller: Use a 1/2" to 1 1/2" nap synthetic roller cover. Do not roll too rapidly as this can cause pinholes or air bubbles.
- Spray: Airless
Pressure, minimum 2500 psi
Tip, minimum .321"
- Priming: After cleaning the surface thoroughly, prime any new, bare surface with Acrylic Clear Primer – 9000.
- Repainting: Acrylic Clear Primer – 9000 may be used as the primer.



PO Box 6256
Mobile AL, 36606
1-800-771-6643

PRODUCT DATA SHEET

Acrylic Wall Coat 2000

WARRANTY

American WeatherStar warrants that the material supplied will meet or exceed physical properties as published. The contractor guarantees that workmanship will be free of defects in coating application. Since performance of previously installed substrate is beyond the control of American WeatherStar or the contractor, requests for additional warranty coverage shall be subject to prior approval by American WeatherStar.

MAINTENANCE

Periodic maintenance of all American WeatherStar products, including cleaning, will ensure extended service life and maintain reflectivity.

TECHNICAL DATA

Two coat system, brush, roller, or spray applied, coverage per coat:	115-160 sq ft/gal 10 - 14 mils wet 4.0 - 6.0 mils dry
<i>Can be applied up to 20 mils wet. Coverage will vary with the substrate and the texture.</i>	
Finish: Flat	0-10 units
Vehicle Type:	Acrylic
VOC (less exempt solvents):	95 g/L
Volume Solids:	42 ± 2%
Weight Solids:	59 ± 2%
Weight:	11.8 lbs. per gallon
Elongation:	325%
Tensile Strength:	340 psi