



PO Box 6256
Mobile AL, 36606
1-800-771-6643

PRODUCT DATA SHEET

Acrylic Clear Primer 9000

DESCRIPTION

Acrylic Clear Primer 9000 is designed to be a bonding primer for concrete block, masonry, and wood surfaces prior to applying the American WeatherStar wall coating.

ADVANTAGES

- Excellent adhesion to various surfaces.
- Easy to use, easy clean up, non-toxic and VOC compliant water based coating.
- Must be top-coated with either Acrylic Coat 2000 or other WeatherStar Coatings top coats.

BASIC USES

Apply to wood, masonry, or concrete block prior to coating with Acrylic Wall Coat 2000.

INSTALLATION

All surfaces to be coated must be cleaned properly. Power washing is recommended. Any existing coating must be checked for good adhesion. Before application, any loosely adhered coating must be removed and bare surfaces must be prepared, cleaned and checked for compatibility.

May be applied by brush, roller or spray, Stir material thoroughly before using. Paint at temperature between 50 degrees F and 95 degrees F. Allow 4 to 6 hours before recoating. Dampness and humidity will directly effect drying time. Clean equipment and area with soap and water.

- Spray: Airless sprayer. 1/2 g.p.m. capacity with a #317 tip
- Brush: Good quality synthetic bristle brush.
- Roller: Short nap roller.

WARRANTY

American WeatherStar warrants that the material supplied will meet or exceed physical properties as published. The contractor guarantees that workmanship will be free of defects in coating application. Since performance of previously installed substrate is beyond the control of American WeatherStar or the contractor, requests for additional warranty coverage shall be subject to prior approval by American WeatherStar.



PO Box 6256
Mobile AL, 36606
1-800-771-6643

PRODUCT DATA SHEET

Acrylic Clear Primer 9000

MAINTENANCE

Periodic maintenance of all American WeatherStar products, including cleaning, will ensure extended service life and maintain reflectivity.

TECHNICAL DATA

Color:	Clear
Viscosity:	1,000 cps
Weight:	8.38 lbs. per gallon
Percent Solids by Weight:	31% ± 2%
Flash Point:	NA
Coverage:	Approximately 200 sq ft per gallon depending on texture of substrate.
Recommended Coverage:	One coat
Min. Surface Application Temp.:	55°F. Do not allow to freeze.
Drying Time:	Will depend on climate conditions. Allow at least 24 hours drying time between coats.